Schlenk TAF GmbH & Co. KG • Barnsdorfer Haupstr. 5 • D-91154 Roth-Barnsdorf • Germany
www.schlenk.com • aluflake@schlenk.de
Director BU TAF: Uğur Çelikkayali, Tel. +49 9171 808 - 238
Application Service: Dr. Sebastian Bergold, Tel. +49 9171 808 - 586, Stephan Krebs, Tel. +49 9171 808 - 315, Dr. Karla Späth, Tel. +49 9171 808 - 801, Irina Safonova, Tel. +371 2000 5721
Sales Department: Andreas Becker, Tel. +49 9171 808 - 262

Technical Ceramics (p.1/4)

Aluminium Powders - wettable

Product Name	Particle Size d_{50} *1 [µm]	Particle Size d_{90} *1 [µm]	Bulk Density *2 [g/cm³]
7002	~ 170	~ 300	0.23 - 0.29
7004	~ 85	~ 175	0.16 - 0.21
7009	~ 40	~ 95	0.11 - 0.15
7110	~ 35	~ 85	0.10 - 0.14
7112	~ 30	~ 70	0.11 - 0.15
7114	~ 28	~ 60	0.10 - 0.14
7210	~ 40	~ 70	0.11 - 0.15
7213	~ 30	~ 50	0.14 - 0.18
77213	~ 20	~ 50	0.14 - 0.18
77004	~ 70	~ 145	0.16 - 0.21
77007	~ 60	~ 130	0.16 - 0.21
77009	~ 40	~ 95	0.15 - 0.19
77010	~ 25	~ 65	0.13 - 0.17
77012	~ 23	~ 60	0.13 - 0.17
77013	~ 22	~ 52	0.12 - 0.16
77014	~ 21	~ 48	0.11 - 0.15
87007	~ 65	~ 120	0.12 - 0.16
87010	~ 35	~ 65	0.11 - 0.15
87012	~ 28	~ 55	0.12 - 0.16
87013	~ 25	~ 45	0.13 - 0.17
87014	~ 23	~ 45	0.11 - 0.15

All powders are available in reaction-delayed versions and are available as DEG-Pastes.

Test Methods: *1 AQSB-044 *2 AQSB-001



Data in this publication is based on careful investigations and is intended for information only. All information shall not be binding, shall carry no warranty as to certain ingredients, as to the fitting for a special purpose, as to the merchantability, or as to the industrial property rights of third parties. Any and all users are obliged to carry out tests on their own authority as well as to check the suitability and the danger of the respective product for a particular application. SCHLENK assumes no liability in this regard; neither to the exactness nor to the completeness of the data. We apply our General Sales Conditions to be found on **www.schlenk.com.** ***CS 10/2026***

Schlenk TAF GmbH & Co. KG • Barnsdorfer Haupstr. 5 • D-91154 Roth-Barnsdorf • Germany
www.schlenk.com • aluflake@schlenk.de
Director BU TAF: Uğur Çelikkayali, Tel. +49 9171 808 - 238
Application Service: Dr. Sebastian Bergold, Tel. +49 9171 808 - 586, Stephan Krebs, Tel. +49 9171 808 - 315, Dr. Karla Späth, Tel. +49 9171 808 - 801, Irina Safonova, Tel. +371 2000 5721
Sales Department: Andreas Becker, Tel. +49 9171 808 - 262

Technical Ceramics (p.2/4)

Aluminium Powders - not wettable

Product Name	Particle Size d_{50} *1 [µm]	Particle Size d_{90} *1 [µm]	Bulk Density *2 [g/cm³]
76004	~ 65	~ 135	0.10 - 0.20
76007	~ 50	~ 110	0.17 - 0.23
76010	~ 30	~ 70	0.14 - 0.18
76011	~ 25	~ 65	0.13 - 0.17
76013	~ 22	~ 50	0.13 - 0.17
76014	~ 21	~ 48	0.12 - 0.16
86013	~ 22	~ 45	0.13 - 0.18

All powders are available in reaction-delayed versions and are available as DEG-Pastes.

Waterborne Pastes - stabilised

Product Name	Particle Size d_{50} *1 [µm]	Particle Size d_{90} *1 [µm]
Aquapor 1000 series	~ 35	~ 110
Aquapor 3000 series	~ 25	~ 85
Aquapor 7000 series	~ 18	~ 50
Aquapor 9000 series	~ 15	~ 37
Aquapor 70004 series	~ 60	~ 125
Aquapor 70007 series	~ 45	~ 110
Aquapor 70010 series	~ 25	~ 65
Aquapor 70013 series	~ 20	~ 50

All pastes are available with different solid content and different reaction delay.

Test Methods: ***1 AQSB-044** ***2 AQSB-001**



Data in this publication is based on careful investigations and is intended for information only. All information shall not be binding, shall carry no warranty as to certain ingredients, as to the fitting for a special purpose, as to the merchantability, or as to the industrial property rights of third parties. Any and all users are obliged to carry out tests on their own authority as well as to check the suitability and the danger of the respective product for a particular application. SCHLENK assumes no liability in this regard; neither to the exactness nor to the completeness of the data. We apply our General Sales Conditions to be found on **www.schlenk.com.** ***CS 10/2026***

Schlenk TAF GmbH & Co. KG • Barnsdorfer Haupstr. 5 • D-91154 Roth-Barnsdorf • Germany
www.schlenk.com • aluflake@schlenk.de
Director BU TAF: Uğur Çelikkayali, Tel. +49 9171 808 - 238
Application Service: Dr. Sebastian Bergold, Tel. +49 9171 808 - 586, Stephan Krebs, Tel. +49 9171 808 - 315, Dr. Karla Späth, Tel. +49 9171 808 - 801, Irina Safonova, Tel. +371 2000 5721
Sales Department: Andreas Becker, Tel. +49 9171 808 - 262

Technical Ceramics (p.3/4)

Solventborne Pastes (Diethylene Glycol) - stabilised

Product Name	Particle Size d_{50} *1 [µm]	Particle Size d_{90} *1 [µm]
DEG/1500 series	~ 35	~ 110
DEG/3500 series	~ 25	~ 85
DEG/7500 series	~ 18	~ 50
DEG/9500 series	~ 15	~ 37
DEG/75004 series	~ 60	~ 125
DEG/75007 series	~ 45	~ 110
DEG/75009 series	~ 40	~ 95
DEG/75010 series	~ 25	~ 65
DEG/75013 series	~ 20	~ 50

All pastes are available with different solid content and different reaction delay.

Solventborne Pastes (Diethylene Glycol) - from wettable powders

Product Name	Particle Size d_{50} *1 [µm]	Particle Size d_{90} *1 [µm]
DEG/77004/77	~ 70	~ 140
DEG/77007	~ 60	~ 130
DEG/77009	~ 40	~ 90
DEG/77010 series	~ 25	~ 65
DEG/77112	~ 25	~ 60
DEG/77013 series	~ 23	~ 50
DEG/77014 series	~ 22	~ 48
DEG/87116/65	~ 14	~ 30

All pastes are available with different solid content and different reaction delay.

Test Methods: ***1 AQSB-044**



Data in this publication is based on careful investigations and is intended for information only. All information shall not be binding, shall carry no warranty as to certain ingredients, as to the fitting for a special purpose, as to the merchantability, or as to the industrial property rights of third parties. Any and all users are obliged to carry out tests on their own authority as well as to check the suitability and the danger of the respective product for a particular application. SCHLENK assumes no liability in this regard; neither to the exactness nor to the completeness of the data. We apply our General Sales Conditions to be found on **www.schlenk.com.** ***CS 10/2026***

Schlenk TAF GmbH & Co. KG • Barnsdorfer Haupstr. 5 • D-91154 Roth-Barnsdorf • Germany
www.schlenk.com • aluflake@schlenk.de
Director BU TAF: Uğur Çelikkayali, Tel. +49 9171 808 - 238
Application Service: Dr. Sebastian Bergold, Tel. +49 9171 808 - 586, Stephan Krebs, Tel. +49 9171 808 - 315, Dr. Karla Späth, Tel. +49 9171 808 - 801, Irina Safonova, Tel. +371 2000 5721
Sales Department: Andreas Becker, Tel. +49 9171 808 - 262

Technical Ceramics (p.4/4)

Calcium Carbonate Compounds

Product Name	Aluminium Content x [%]	Particle Size d_{50} *1 [µm]	Blaine/ Water Coverage *5 [g/cm³]
CaCO3/7004/x	10/20	~ 85	min. 7 000
CaCO3/7114/x	10/20	~ 28	min. 22 500
CaCO3/77004/x	10/20	~ 70	min. 7 000
CaCO3/77009/x	10/20	~ 40	min. 13 000
CaCO3/77014/x	10/20	~ 21	min. 19 000
CaCO3/76004/x	10/20	~ 65	min. 3 500
CaCO3/290/x	10/20	~ 10	min. 35 000
CaCO3/290R/x	10/20	~ 10	min. 35 000
CaCO3/U290XR/x	10/20	~ 10	min. 35 000
CaCO3/260R/x	10/20	~ 25	min. 18 000
CaCO3/260XR/x	10/20	~ 25	min. 18 000
CaCO3/U320R/x	10/20	~ 55	min. 8 000

Other compounds are possible.

Test Methods: *1 AQSB-044 *5 AQSB-010/014



Data in this publication is based on careful investigations and is intended for information only. All information shall not be binding, shall carry no warranty as to certain ingredients, as to the fitting for a special purpose, as to the merchantability, or as to the industrial property rights of third parties. Any and all users are obliged to carry out tests on their own authority as well as to check the suitability and the danger of the respective product for a particular application. SCHLENK assumes no liability in this regard; neither to the exactness nor to the completeness of the data. We apply our General Sales Conditions to be found on **www.schlenk.com.** ***CS 10/2026***